

FuRe Industrial (Shanghai) CO., LTD.

379#, Xin Sheng Road, Shanghai 201712
Tel: +86-21-33884598 Fax: +86-21-59211909

Datasheet

Issued Nov. 2014

锐腾 ReTeng[®] VM-70-WT01

● Description

Application: O-ring, gasket, hose
Form and Color: Sheet
White

● Compound Properties

Compression Moulding, 5 minutes at 180°C
Post-Curing, 4 hours at 180°C

Tensile Properties, T2 at 23°C

Tensile Strength	MPa	19
Elongation at break	%	290

Hardness , 1 second at 23°C	Shore A	73
-----------------------------	---------	----

Tear Angle at 23°C	kN/m	39
--------------------	------	----

Compression set, 22 hours at 175°C	%	18
------------------------------------	---	----

● Test Procedures

Property Measured	Test Procedure
Tensile Properties	ASTM D412
Hardness Shore A	ASTM D1414
Compression set	ASTM D395

The information set forth herein is furnished free of charge and is based on technical data that FuRe Industrial believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. Since conditions of product use and disposal are outside of our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information.

锐腾 ReTeng[®] is a trademark of FuRe Industrial.
Copyright © 2012 FuRe Industrial. All Rights Reserved.